

gloveon Paloma



Nitrile Exam Gloves Powder Free, Standard Cuff

To don **Paloma XS** is like putting on a 2nd skin. Its absolute tactility commends it to delicate procedures and jobs plus an assured tensile strength and resistance to chemical expected of a nitrile glove. You owe it to yourself to try this exceptional nitrile glove from **GloveOn**.



GloveOn Paloma XS		
Length (mm)	≥ 230	
Thickness Measurements (mm)		
Palm (centre of Palm)	0.10 ± 0.02	
Finger (13mm ± 3mm from tip)	0.11 ± 0.02	
Physical Properties		
Tensile Strength (MPa)	Before Ageing ≥ 14	After Ageing ≥ 14
Elongation (%)	≥ 500	≥ 400
Inspection Levels & AQL		
Watertightness	G1	1.50
Physical Dimensions	S2	4.00
Tensile Strength	S2	4.00
Visual Inspection (Major)	S4	2.50
Visual Inspection (Minor)	S4	4.00
Particulate Residue	N = 5	≤ 2mg/glove

Chemotherapy Drugs and Concentration (Tested for Resistance to Permeation by Chemotherapy Drugs as per ASTM D6978-05-Test Report PN 92390)	Minimum Breakthrough Detection Time (minutes)
Carmustine (BCNU), 3.3mg/ml (3,300 ppm)	16.2 minutes
Cisplatin, 1.0mg/ml (1,000 ppm)	>240 minutes
Cyclophosphamide (Cytoxan), 20.0mg/ml (20,000 ppm)	>240 minutes
Dacarbazine (DTIC), 10.0mg/ml (10,000 ppm)	>240 minutes
Doxorubicin Hydrochloride, 2.0mg/ml (2,000 ppm)	>240 minutes
Etoposide (Toposar), 20.0mg/ml (20,000 ppm)	>240 minutes
Fluorouracil, 50.0mg/ml (50,000 ppm)	>240 minutes
Methotrexate, 25.0mg/ml (25,000 ppm)	>240 minutes
Mitomycin C, 0.5mg/ml (500 ppm)	>240 minutes
Paclitaxel (Taxol), 6.0mg/ml (6,000 ppm)	>240 minutes
Thiotepa, 10.0mg/ml (10,000 ppm)	28.4 minutes
Vincristine Sulfate, 1.0mg/ml (1,000 ppm)	>240 minutes

WARNING: Carmustine and Thiotepa, at the tested concentration, degraded at 16.2 minutes and 28.4 minutes, respectively.
The safe use of gloves in chemotherapy treatment is solely the decision of clinicians authorised to make such decision.

GLOVE SIZES

- X-SMALL
- SMALL
- MEDIUM
- LARGE
- X-LARGE

FEATURES

- Fingertip textured
- Powder free
- Not made with natural rubber latex
- Chemo drugs tested
- Lab chemical tested
- Ambidextrous
- Violet blue colour
- Food Safe

PACKAGING

- 100 gloves per box
- 10 boxes per carton

REGULATORY COMPLIANCE

TGA - ARTG 164563, FDA 510(k),
MDD 93/42/EEC, REACH,
ROHS Directive 2002/95/EC,
EC 10/2011,
REGULATION (EC) No 1935/2004,
PPE Regulation (EU) 2016/425

STANDARDS

ASTM D6319, EN455 part 1, 2, 3 & 4, EN
1186, EN 13130, CEN/TS 14234,
EN 420: 2003+A1: 2009,
EN ISO 374 - 1:2016, EN ISO 374 - 5:2016

MANUFACTURING ACCREDITATIONS ISO

- 9001:2008
- ISO 13485:2003
- EN ISO 13485:2012

A brand by



10, Lotissement Bellevue
Avenue Jean Moulin – 63200 Mozac
Tél. : +33 (0)9 51 62 09 25 - Fax: +33 (0)9 51 62 09 25

Code APE : 519B – Numéro Siret : 495 246 811 00014
Numéro TVA Intracommunautaire : FR 78 495 246 811



Protection Always On

gloveon Paloma



Nitrile Exam Gloves Powder Free, Standard Cuff

Like the purity of a white Dove, **Paloma L**, our white nitrile gloves offers the elegance of touch and feel with strength and dexterity needed for the delicate procedure and jobs.



GloveOn Paloma L		
Length (mm)	≥ 230	
Thickness Measurements (mm)		
Palm (centre of Palm)	0.10 ± 0.02	
Finger (13mm \pm 3mm from tip)	0.11 ± 0.02	
Physical Properties	Before Ageing	After Ageing
Tensile Strength (MPa)	≥ 18	≥ 16
Elongation (%)	≥ 500	≥ 400
Inspection Levels & AQL	Inspection Level	AQL
Watertightness	G1	1.50
Physical Dimensions	S2	4.00
Tensile Strength	S2	4.00
Visual Inspection (Major)	S4	2.50
Visual Inspection (Minor)	S4	4.00
Particulate Residue	N = 5	$\leq 2\text{mg/glove}$

Chemotherapy Drugs and Concentration (Tested for Resistance to Permeation by Chemotherapy Drugs as per ASTM D6978-05 Test Report PN 116668)	Minimum Breakthrough Detection Time (minutes)
Carmustine (BCNU), 3.3mg/ml (3,300 ppm)	16.2 minutes
Cisplatin, 1.0mg/ml (1,000 ppm)	>240 minutes
Cyclophosphamide (Cytosan), 20.0mg/ml (20,000 ppm)	>240 minutes
Dacarbazine (DTIC), 10.0mg/ml (10,000 ppm)	>240 minutes
Doxorubicin Hydrochloride, 2.0mg/ml (2,000 ppm)	>240 minutes
Etoposide (Toposar), 20.0mg/ml (20,000 ppm)	>240 minutes
Fluorouracil, 50.0mg/ml (50,000 ppm)	>240 minutes
Methotrexate, 25.0mg/ml (25,000 ppm)	>240 minutes
Mitomycin C, 0.5mg/ml (500 ppm)	>240 minutes
Paclitaxel (Taxol), 6.0mg/ml (6,000 ppm)	>240 minutes
Thiotepa, 10.0mg/ml (10,000 ppm)	28.4 minutes
Vincristine Sulfate, 1.0mg/ml (1,000 ppm)	>240 minutes

WARNING: Carmustine and Thiotepa, at the tested concentration, degraded at 16.2 minutes and 28.4 minutes, respectively.
The safe use of gloves in chemotherapy treatment is solely the decision of clinicians authorised to make such decision.

GLOVE SIZES

- X-SMALL
- SMALL
- MEDIUM
- LARGE
- X-LARGE

FEATURES

- Fingertip textured
- Powder free
- Not made with natural rubber latex
- Chemo drugs tested
- Lab chemical tested
- Ambidextrous
- Standard cuff
- Violet blue colour
- Food Safe

PACKAGING

100 gloves per box
10 boxes per carton

REGULATORY COMPLIANCE

TGA - ARTG 164563, FDA 510(k),
MDD 93/42/EEC, REACH,
ROHS Directive 2002/95/EC, EC 10/2011,
REGULATION (EC) No 1935/2004,
PPE Regulation (EU) 2016/425

STANDARDS

ASTM D6319, EN455 part 1, 2, 3 & 4, EN
1186, EN 13130, CEN/TS 14234,
EN 420: 2003+A1: 2009, EN ISO 374 -
1:2016, EN ISO 374 - 5:2016

MANUFACTURING ACCREDITATIONS

ISO 9001:2008
ISO 13485:2003
EN ISO 13485:2012

A brand by



10, Lotissement Bellevue
Avenue Jean Moulin – 63200 Mozac
Tél. : +33 (0)9 51 62 09 25 - Fax.: +33 (0)9 51 62 09 25

Code APE : 519B – Numéro Siret : 495 246 811 00014
Numéro TVA Intracommunautaire : FR 78 495 246 811



Protection Always On